



# HIGH GLOSS

## SPECIFICATIONS AND TECHNICAL DATA SHEET

### Product

High Gloss compression molded products.

### Manufacturer

Swan is headquartered in St. Louis, Missouri with manufacturing in Centralia, Illinois.

### Product Composition

High Gloss is a compression-molded with a durable baked-on industrial coating with a very high shine. It is non-porous material that will not mold or mildew.

### Colors

Veritek is available in a White (010), Bisque (018) and Bone (037).

### Warranties

High Gloss bath walls are covered by a limited lifetime warranty for residential applications. Swan offers a five year Limited Warranty on bath walls for commercial applications. Complete details on these warranties are available on our website, Swanstone.com.

### Maintenance

The High-Gloss finish is stain and abrasion resistant. The finish, however, requires reasonable care. Clean regularly with common household liquid cleaners and a sponge or soft cloth. Do not use abrasive cleaners or scouring pads. Do not use "leave on" cleaning products, such as automatic spray shower cleaners. Prolonged contact with harsh chemicals could have an adverse reaction over time and discolor surfaces.

### Limitations

Veritek products are not recommended for exterior use. Follow all recommended installation procedures provided by the manufacturer.

### Finish

The High-Gloss finish is a baked-on industrial coating with a very high shine (gloss reading of 85). To maintain the high shine, abrasive cleansers should not be used with these products.

### Application

High-Gloss is appropriate for any interior bath and shower wall application.

### Limitations

High-Gloss products are not recommended for exterior use. Follow all recommended installation procedures provided by the manufacturer.

### Cost

Cost varies with product category. Contact your local distributor for applicable costs.

### Installation

Consult the specific product installation manual for step-by-step installation procedures. All manuals are available at our website, Swanstone.com, or through Swan or your local distributor.

PROPERTY	TYPICAL RESULT	TEST
Impact Resistance on wall surrounds	No cracks (10 lbs dropped 48" on unit)	ANSI-Z 124.1.2
Loads Test	No cracks (25 lbs. for one minute repeated at 2 minute intervals)	ANSI-Z 124.1.2
Izod Impact		ASTM D256
Method A (with notch) Method E	1.6 Ft/LB/In 2.1/Ft/LB/In	
Stain Resistance	Passes	ANSI-Z 124.1.2
Cigarette Resistance	Passes	ANSI-Z 124.1.2
Boiling Water Resistance	Passes	ANSI-Z 124.1.2
Chemical Resistance		NEMA LD3
Color Fastness Test		ASTMD3-3.08
Wear and Cleanability	Passes	ANSI-Z 124.1.2